CIVIL QUALITY CONSULTANTS & ENGINEERS

(Buildings Geo-Tech & Highway Materials Testing Laboratory)
An ISO 9001: 2008 Certified Company

JAS-ANZ
ISO 9001:2000 CERTIFIED

Job No.: CQCE/BBMP/SKSIPL/W.No.17/2018-19

21.01.2019

TEST REPORT ON COMPRESSIVE STRENGTH OF CONCRETE CUBES

Client : **Executive Engineer,** Rajarajeshwari Nagara Division, BBMP, Bangalore.

Agency : **Sri. B.N Girish**
SKS Infrastructure Pvt. Ltd.
#180, K.G Nagar, 1st Main Road, Bangalore-560019.

Name of the work : Construction of Dhyana Mandira at JP Park Phase II in Ward No.17.

Reference : EE/RRND/Wo. No/000074/2017-18 dated:08.02.2018

Sample ID : Cement Concrete - RCC Wall

Size of cubes : 150mmx150mmx150mm

Cross Sectional Area : 22500 mm^2

Technical Reference : IS: 516-1959 (Reaffirmed 2008)

Grade of Concrete : M_{25}

Compressive Strength as on : 28^{th} day

Sl.No.	Date of casting	Date of testing	Weight of cube (Kg)	Failure load (KN)	Compressive strength (N/mm^2)
1	24.12.2018	21.01.2019	8.365	625.2	27.79
2	24.12.2018	21.01.2019	8.385	610.6	27.14
3	24.12.2018	21.01.2019	8.375	636.1	28.27

Note:
1. The report shall not be reproduced, except in full, without the written approval of the laboratory.
2. The results indicated above are based on the tests carried out on the samples received in the laboratory.
3. Any Query regarding the report must be reported within 30 days from the date of testing.

ಸಮಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು
ಯಶವಂತಪುರ ಉಪ ವಿಭಾಗ
ಬಿಬಿಎಂಪಿ ಬೆಂಗಳೂರು ಮಹಾನಗರ ಪಾಲಿಕೆ

For CIVIL QUALITY CONSULTANTS & ENGINEERS

Authorised Signatory

Office & Laboratory : # 133, Bhuvaneshwarinagar, Dodda Basti Main Road, Bangalore - 560 056.
e-mail:civilqualityconsultants@gmail.com Ph: 080-23240644 / Mob: 8553518550

Scanned by CamScanner

CIVIL QUALITY CONSULTANTS & ENGINEERS

(Buildings Geo-Tech & Highway Materials Testing Laboratory)
An ISO 9001: 2008 Certified Company

JAS-ANZ
ISO 9001:2000 CERTIFIED

Job No.: CQCE/BBMP/SKSIPL/W.No.17/2018-19

31.12.2018

TEST REPORT ON COMPRESSIVE STRENGTH OF CONCRETE CUBES

Client : **Executive Engineer,** Rajarajeshwari Nagara Division, BBMP, Bangalore.

Agency : **Sri. B.N Girish**
SKS Infrastructure Pvt. Ltd.
#180, K.G Nagar, 1st Main Road, Bangalore-560019.

Name of the work : Construction of Dhyana Mandira at JP Park Phase II in Ward No.17.

Reference : EE/RRND/Wo. No/000074/2017-18 dated:08.02.2018

Sample ID : Cement Concrete - RCC Wall

Size of cubes : 150mmx150mmx150mm

Cross Sectional Area : 22500 mm^2

Technical Reference : IS: 516-1959 (Reaffirmed 2008)

Grade of Concrete : M_{25}

Compressive Strength as on : 7^{th} day

Sl.No.	Date of casting	Date of testing	Weight of cube (Kg)	Failure load (KN)	Compressive strength (N/mm^2)
1	24.12.2018	31.12.2018	8.282	399.5	17.76
2	24.12.2018	31.12.2018	8.269	415.8	18.48
3	24.12.2018	31.12.2018	8.248	421.6	18.74

Note:
1. The report shall not be reproduced, except in full, without the written approval of the laboratory.
2. The results indicated above are based on the tests carried out on the samples received in the laboratory.
3. Any Query regarding the report must be reported within 30 days from the date of testing.

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು
ರಾಜರಾಜೇಶ್ವರಿ ನಗರ ಉಪ ವಿಭಾಗ
ಬೃಹತ್ ಬೆಂಗಳೂರು ಮಹಾನಗರ ಪಾಲಿಕೆ

For CIVIL QUALITY CONSULTANTS & ENGINEERS

Authorised Signatory

Scanned by CamScanner

CIVIL QUALITY CONSULTANTS & ENGINEERS

(Buildings Geo-Tech & Highway Materials Testing Laboratory)
An ISO 9001: 2008 Certified Company

JAS-ANZ
ISO 9001:2000 CERTIFIED

Job No.: CQCE/BBMP/SKSIPL/W.No.17/2018-19

21.01.2019

TEST REPORT ON COMPRESSIVE STRENGTH OF CONCRETE CUBES

Client : **Executive Engineer,** Rajarajeshwari Nagara Division, BBMP, Bangalore.

Agency : **Sri. B.N Girish**
SKS Infrastructure Pvt. Ltd.
#180, K.G Nagar, 1st Main Road, Bangalore-560019.

Name of the work : Construction of Dhyana Mandira at JP Park Phase II in Ward No.17.

Reference : EE/RRND/Wo. No/000074/2017-18 dated:08.02.2018

Sample ID : Cement Concrete - RCC Wall

Size of cubes : 150mmx150mmx150mm

Cross Sectional Area : 22500 mm^2

Technical Reference : IS: 516-1959 (Reaffirmed 2008)

Grade of Concrete : M_{25}

Compressive Strength as on : 28^{th} day

Sl.No.	Date of casting	Date of testing	Weight of cube (Kg)	Failure load (KN)	Compressive strength (N/mm^2)
1	24.12.2018	21.01.2019	8.365	620.3	27.57
2	24.12.2018	21.01.2019	8.380	619.5	27.53
3	24.12.2018	21.01.2019	8.382	638.1	28.36

Note:

1. The report shall not be reproduced, except in full, without the written approval of the laboratory.
2. The results indicated above are based on the tests carried out on the samples received in the laboratory.
3. Any Query regarding the report must be reported within 30 days from the date of testing.

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು
ಯಲಹಂಕಪುರ ಉಪ ವಿಭಾಗ
ಬೃಹತ್ ಬೆಂಗಳೂರು ಮಹಾನಗರ ಪಾಲಿಕೆ

For CIVIL QUALITY CONSULTANTS & ENGINEERS

Authorised Signatory

Office & Laboratory : # 133, Bhuvaneshwarinagar, Dodda Basti Main Road, Bangalore - 560 056.
e-mail:civilqualityconsultants@gmail.com Ph: 080-23240644 / Mob: 8553518550

Scanned by CamScanner